



Product Finishes

CC-T6

SHER-WOOD® Catalysts

KEMVAR® Catalyst..... V66V21
Precat Catalyst V66V22

Super KEMVAR® Catalyst V66V26
Hi-Bild Precat Catalyst..... V66V3

F3 KEMVAR® Catalyst..... V66V70
POLANE® T60 Catalyst..... V66V90

For other characteristics and method of use, please refer to the technical data sheets relating to part A.

REX Number	Products Used With	TDS Reference	Amount of catalyst per TDS	Pot Life	Catalyst Shelf Life-Unopened
V66V21 SHER-WOOD® KEMVAR® Catalyst	Hi Solids Vinyl Sealer T67F5	CC-F44	1.5 % or 2 oz/ gallon	24 hours	24 months
	KEMVAR® LF Water White CV V84F96 Series	CC-F55	4 oz/gallon	24 hours	
	KEMVAR® CV V84V60 Series	CC-F17A	3% or 3.84 oz/gallon	24 hours	
	Water White CV V84V80 Series	CC-F24	3% or 3.84 oz/gallon	24 hours	
	KEMVAR® Plus CV H66W51 Series	CC-F70	6.2% or 8 oz/gallon	24 hours	
	Kemvar Plus Sealer E63W50 Series	CC-F69	4.7 % or 6 oz/gallon	24 hours	
V66V22 SHER-WOOD® Precat Catalyst	Fast Dry Vinyl Sealer T67F6	CC-F53	1.2 % or 1.5 oz/ gallon	6 months	24 months
	Catalyzed Lacquer Precat T77C35 Series	CC-F43	1.2 % or 1.5 oz/ gallon	6 months	
	F3 Precat Primer Surfacer E63W330 Series	CC-F83	0.8% or 1 oz/gallon	4 months	

An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.paintdocs.com.

REX Number	Products Used With	TDS Reference	Amount of catalyst per TDS	Pot Life	Catalyst Shelf Life - Unopened
V66V26 SHER-WOOD® Super KEMVAR® Catalyst	Kemvar® Vinyl Sealer T67F7	CC-F54	2% or 2.56 oz/gallon	24 hours	24 months
	Vinyl Sealer T67F3	CC-F20	2% or 2.56 oz/gallon	24 hours	
	Acrylic Conversion Coating T77C60 Series	CC-F52	4 oz/gallon	6 months	
	Catalyzed Lacquer T77C30 Series	CC-F21	3% or 3.84 oz/gallon	30 days	
	F3 Hi Bild Precat Lacquer T85C355 Series	CC-F78	1.5% or 2 oz/gallon	4 months	
	Super Kemvar® "C" Catalyzed Vinyl Coating T77F4	CC-F8	5% or 6.4 oz/gallon	3 days	
	Super Kemvar® "M" Topcoat T77F47 Series	CC-F22	5% or 6.4 oz/gallon	5 days	
	F3 Hi Bild Precat White Lacquer T85W310 Series	CC-F82	1.5% or 2 oz/gallon	4 months	
	F3 Kemvar® Plus CV V85W351 Series	CC-F81	5% or 6.4 oz/gallon	5 days	
	F3 Kemvar® Plus Surfacer E63W350 Series	CC-F80	5% or 6.4 oz/gallon	5 days	
	Vinyl Basecoat System P63W9 Series	CC-F35	2% or 2.56 oz/gallon	24 hours	
	White Vinyl Sealer P63W2	CC-F26	2% or 2.56 oz/gallon	24 hours	
V66V3 SHER-WOOD® Hi-Bild PreCat Catalyst	Hi Bild Precat Lacquer T77C55 Series	CC-F57	3 oz/gallon	4 months	24 months
	White Hi Bild Precat Lacquer T77W10 Series	CC-F60	3 oz/gallon	3 months	
	Precat Primer Surfacer E63W30	CC-F59	4 oz/gallon	3 months	
V66V70 SHER-WOOD® F3 KemVar® Catalyst	F3 KEMVAR® Sealer T85F300	CC-F76	2% or 2.56 oz/gallon	24 hours	12 months
	F3 KEMVAR® Varnish V85V300 Series	CC-F73	2% or 2.56 oz/gallon	24 hours	
V66V90 POLANE® T60 Catalyst	Polyurethane Sealer T63F10	CC-F72	9:1 ratio	4 hours	12 months
	Polyurethane T73V120 Series	CC-F71	9:1 ratio	5 hours	

An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.paintdocs.com.

FOR INDUSTRIAL SHOP APPLICATION

Thoroughly review product label and Safety Data Sheet (SDS) for safety and cautions prior to using this product. Regulatory documents are available from your local Sherwin-Williams facility, or at www.paintdocs.com. Please direct any questions or comments to your local Sherwin-Williams facility.

Note: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, The Sherwin-Williams Company cannot make any warranties as to the end result.