



General Industrial Coatings

CC-A70

Duraspar™ Prime High Speed 2K Epoxy

Gray E61AC161 Catalyst V66VC256

DESCRIPTION

Duraspar™ Prime High Speed, E61AC161, is an AD/FD, VOC compliant, two component coating suitable for use as a primer on metal substrates.

Advantages:

- Excellent cure speed
- Fast dry time compared to traditional epoxy primers.
- Superior corrosion resistance
- Excellent adhesion to various metals
- No Induction time
- Wet-on-wet and wet-on-dry application with 2K solventborne urethane topcoats
- Approved to UL 1332 when topcoated with Polane 8890.
- Complies with 2.8 VOC solvent emissions

CHARACTERISTICS

Component A: E61AC161
Component B: V66VC256

Weight/Gallon (lbs.):
 E61AC161 12.6 ± 0.2
 V66VC256 7.6 ± 0.2
 Admixed 12.3 ± 0.2

Weight Solids:
 E61AC161 72.9 ± 2 %
 V66VC256 65.1 ± 2 %
 Admixed 71.3 ± 2 %

Volume Solids:
 E61AC161 49.0 ± 2 %
 V66VC256 60.6 ± 2 %
 Admixed 50.5 ± 2 %

Mixing Ratio (by volume):
 E61AC161 10 Parts
 V66VC256 1 Parts

Potlife (at 77 °F): 4 hours

Viscosity (at 77 °F):
 E61AC161 20-25 secs., #2 Zahn Cup**
 Admixed 20-25 secs., #2 Zahn Cup**
 **Signature Series

VOC (less exempt solvents):
 E61AC161 3.0 lbs./gal. 359 g/l
 V66VC256 2.6 lbs./gal. 317 g/l
 Admixed 2.8 lbs./gal. 337 g/l

HAPS:
 E61AC161 0.21 lbs./gal. solids
 V66VC256 0.00 lbs./gal. solids
 Admixed 0.18 lbs./gal. solids

Flash Point (Pensky Martens Closed Cup):
 E61AC161 76 °F
 V66VC256 53 °F
 Admixed 76 °F

Vol. Solids at Gun: 50.5 % at 2.8 VOC

Recommended Film Thickness:
 Mils Wet 3.0-4.0
 Mils Dry 1.5-2.0
 Mils Dry, Maximum 3.0

Coverage: 540 ft.²/gal. at 1.5 mils DFT (theoretical)

Cure:

Wet-on-Wet: Allow primer to flash 10-20 mins. prior to topcoat application.
Air Dry: Allow the coated part to cure ≥16 hours at 70 °F indoors before placing the part outdoors.
Force Dry: 10 mins. flash, 30 mins. at 150 °F

Drying: (1.5-2.0 mils @ 77 °F / 50% RH)
 To Touch 30 minutes
 Tack Free 60 minutes
 To Handle 3 hours
 Total (Full Properties) 7 days

Performance Tests

Substrate: 24 gauge Bonderite® 1000 P99X cold rolled steel panels
 Primer: 1.8 mils DFT, E61AC161
 Cure: 14 days

Salt Spray Test (primer only)
 (ASTM B117) 500 hours
 1/16" creep maximum
 no blisters

Sanding/Scuffing: If parts have been stored for longer than 72 hours after priming, they must be scuffed or sanded before top coating to ensure removal of any accumulated dust/dirt.

Recommended Storage: Inside, sealed container, 60-95 °F (15-35° C), 0-90% relative humidity, protected from rain & snow.

Package Life: 12 months from date of manufacture

APPLICATION

Typical Setups

To achieve full performance, the product must be mixed until completely homogeneous with a static or mechanical mixer. If using proportionating equipment product, performance needs to be verified. For specific equipment questions, please contact your local Sales Representative or your local Sherwin-Williams facility.

* VOC Compliance limits vary from state to state; please consult local Air Quality rules and regulations.

An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.PaintDocs.Com.

Reduction: No additional solvents or additives should be added to the paint.

This product is normally applied without reduction. If reduction is needed to optimize application, R6K18 (Butyl Acetate), R6K38 (T-Butyl Acetate), or similar solvent can be used.

Substrate Preparation: All substrates should be free of mold release, oil, grease, dirt, fingerprints, drawing compounds, surface passivation treatments and any other contaminants to ensure optimum adhesion and coating performance.

Steel (CRS & HRS), Iron & Castings: Remove rust, mill scale, and oxidation products. For best results, treat the surface with a proprietary surface chemical treatment of zinc or iron phosphate to improve corrosion protection.

NOTE: Substrate, paint and air temperature must be in range of 70-120 °F. The substrate must be at least 5 °F above the dew point. **If applying at <70 °F, the intercoat adhesion needs to be verified.**

May be applied by: Conventional Spray
Airless Spray
Air Assisted Airless Spray
Electrostatic Spray
HVLP Spray

Conventional Spray:
Atomizing Air Pressure 30-50 psi
Fluid Delivery Rate 8-12 oz./min.
Tip 0.1-1.5 mm

Airless Spray:
Fluid Pressure 1,800-2,700 psi
Tip 0.011-0.015 in

Air Assisted Airless Spray:
Atomizing Air Pressure 30-50 psi
Fluid Pressure 800-1,200 psi
Tip 0.011-0.015 in

Electrostatic Spray:
Resistivity 0.6 megaohms
Atomizing Air Pressure 30-50 psi
Fluid Delivery Rate 8-12 oz./min.
Tip 0.1-1.5 mm

HVLP Spray:
Atomizing Air Pressure Max 10 psi at cap
Fluid Delivery Rate 8-12 oz./min.
Tip 0.8-1.2 mm

Equipment/application guidelines are only guidelines. Individual application and process parameters will dictate exact requirements.

Cleanup: Clean tools/equipment immediately after use with ketones or acetates.

Follow manufacturer's safety recommendations when using any solvent.

ADDITIONAL INFORMATION

- DO NOT VARY CATALYST RATIO.**
The catalyst ratio has been established for optimum hardness, flexibility, gloss, and chemical & solvent resistance.
- On sandblasted surfaces, apply sufficient film thickness to fully protect the blast profile. This is typically 1 mil more than the blast profile.
- Equipment/application guidelines are only guidelines and individual application/process parameters will dictate exact requirements.
- Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion and compatibility prior to full scale application.



When topcoated with Polane 8890 Polyurethane Enamel, Duraspar Prime High Speed 2K Epoxy Primer, E61AC161, is an Underwriters Laboratory 1332 Recognized Component.
File Number: 10711, Vol 5

CAUTIONS

Thoroughly review the product label for safety and cautions prior to using this product. A Safety Data Sheet (SDS) and an Environmental Data Sheet (EDS) are available from your local Sherwin-Williams Facility or www.PaintDocs.Com. Please direct any questions or comments to your local Sales Representative or your local Sherwin-Williams facility.

DO NOT TAKE INTERNALLY

KEEP OUT OF THE REACH OF CHILDREN

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review the product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.PaintDocs.Com.

Please direct any questions or comments to your local Sherwin-Williams facility.

All trademarks are the property of their respective owners.

Note: Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application, which are not known or under our control, The Sherwin-Williams Company cannot make any warranties as to the end result.

Note:

All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' [Terms and Conditions of Sale](#). Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.**

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.